

# Technical Data Sheet



## Injection Mortar FIS V 360 S/ FIS V 950 S

Prepared on: 28.04.2009  
Version: 4.0

Reviewed on: 05.12.2017

Printing Date: 05.12.2017  
Page: 1 von 1

Product Description: High performance hybrid mortar in shuttle cartridge,  
styrene free  
Colour: grey

### Technical Data:

Product Data	Testing Method	Results
--------------	----------------	---------

Stability		
UV-resistance (sunlight)		resistant
Temperature resistance		120 °C
Water resistance		resistant
Water absorption		after 14 days: 0.8 %
Cleaning agents		1 % tenside solution no effects
Long-term behaviour (Freezing and thawing resistance)	EOTA part 5	approved suitability for outside applications

Physical properties		
Shrinkage		< 0.9 %
Hardness Shore A		after 45 min: 83
Density		1.6 - 1.8 g/cm <sup>3</sup>
Thermal conductivity		0,73 W/mK
Contact resistance		1,8 x 10 <sup>12</sup> Ωcm

Workability features		
Viscosity (20 °C)	Brookfield (Sp.7) 10 U/min	110 – 150 Pas
Open time (10 – 20 °C)		5 min
Curing time (10 – 20 °C)		60 min
Shelf life		18 months